



TAILS

POLYAMIDE (NYLON) TAILS

OCIMF required tail for gas tankers

GENERAL

- High abrasion resistance
- Excellent weight/tenacity ratio
- Easy to splice
- Rot-proof
- OCIMF approved

FEATURES

- **Materials:** Polyamide
- **Construction:** 8 strand
- **Color or rope:** White
- **Approx. Spec. Density:** 1.14 non coating
- **Melting point:** 215 °C
- **Abrasion Resistance:** Very good
- **UV Resistance:** excellent
- **Temperature resistance:** workable in sub-zero temperatures
- **Chemical resistance:** good, except in presence of acids
- **Dry & wet conditions:** can be stowed wet

POLYAMIDE (NYLON)					
Dia	Circ.	Dia	Min. Break Load		Weight
mm	"	"	tf	kN	kg/100m
6	3/8	1/4	0.75	7.4	2.25
8	1	5/16	1.35	13.2	4
10	1 1/4	7/16	2.08	20.4	6.2
12	1 1/2	1/2	3	29.4	8.9
14	1 3/4	9/16	4.1	40.2	12.2
16	2	5/8	5.3	52	15.8
18	2 1/4	3/4	6.7	65.7	20
20	2 1/2	13/16	8.3	81.4	24.5
22	2 3/4	7/8	10	98	30
24	3	1	12	118	35.5
26	3 1/4	1 1/16	14	137	42
28	3 1/2	1 1/8	15.8	155	48.5
30	3 3/4	1 1/4	17.7	174	55.5
32	4	1 5/16	20	196	63
36	4 1/2	1 1/2	24.9	244	80
40	5	1 5/8	30	294	99
44	5 1/2	1 3/4	35	351	120
48	6	2	42	412	142
52	6 1/2	2 1/8	48.8	479	166
56	7	2 1/4	56	549	193
60	7 1/2	2 1/2	63.8	626	221
64	8	2 5/8	72	706	252
68	8 1/2	2 3/4	80.1	792	284
72	9	3	90	882	319
76	9 1/2	3 1/8	100	979	355
80	10	3 1/4	110	1078	394
88	11	3 5/8	131	1284	477
96	12	4	154	1510	568
104	13	4 1/4	182	1786	666
112	14	4 5/8	210	2061	772
120	15	5	240	2355	887
128	16	5 1/4	272	2668	1010
136	17	5 4/7	306	3002	1140

